

Platform GPTM

Premium Gypsum Skimcoat

PACKAGING

- 10 lb (4.5 kg) resealable plastic pouch
- 25 lb (11.3 kg) bag kraft paper, double wall bag

SUITABLE SUBSTRATES

- Fast track gypsum concrete
- Fast dry skimcoat over wood

Platform GPTM is a premium gypsum based skimcoat designed for use over gypsum concrete, wood, and other surfaces. Platform GP's polymer modified formula allows for a creamier feel under the trowel, enhanced bond, and superior dry time.

Features

- › Smooth feel on the trowel
- › Fast drying
- › Great for gypsum concrete repair

Properties

Working Time		About 20 minutes	
Setting Time		About 30 minutes	
Coverage	As a skim coat	10 lb	25lb
		100 - 300 ft ²	250 - 750ft ²
	1/8" (3mm)	30 - 36 ft ²	75 - 90 ft ²
	1/4" (6mm)	15 - 18 ft ²	37.5 - 45 ft ²
*Coverage Rates are approximate and for estimating purposes only. Actual product coverage on site will vary according to substrate, applicator and application.			
Thickness		Feather edge to 1 inch (25 mm)	
Ratio		5.5 qts. of water to 25 lb. bag 2.25 qts. of water to 10 lb. bag	
Application Conditions		Dry, interior environment above 50°F (10°C)	
Color		White	
Admixtures		Potable water	

All specifications were tested in laboratory conditions: 70°F in a controlled environment using our approved water content. Changing the temperature, or mixing ratios, or the environment can effect these specifications. Call Technical Services if you have any questions.

LEED Credit Platform GP may contribute to LEED certification of projects as follows:

AREA	CREDIT	CATEGORY	HOW
Indoor Environmental Quality	EQ 4.2	Low Emitting Materials	VOC content 0g/l (calculated)
Materials & Resorces	MR 4.1 4.2	Recycled Content	0%
Materials & Resorces	MR 5.1	Regional Manufactured Material	Cleveland, OH

Preparation & Application

FOR PROFESSIONAL USE ONLY

Surface Preparation

Concrete Floors

All concrete must be sound, stable, clean and free of any bond breaking materials (silicates, curing compounds, laitance, dirt). Mechanically remove weak surfaces, and any contaminants to sound concrete. Priming is not required. Apply from feather edge to 1" in depth. Platform GP is not recommended for use on on-grade and below-grade concrete slabs. Consult Technical Services for details.

Adhesive Residue

Non-soluble adhesives must be scraped to a well bonded residue. Water soluble and pressure sensitive adhesives must be removed mechanically to the substrate. Verify type of adhesive prior to mechanical removal to ensure adhesive containing asbestos is not introduced into the environment. Follow all local, state and federal laws for removal and disposal of adhesive or flooring materials containing asbestos. Test to ensure any existing adhesive will not bleed through to new adhesive, or finished flooring. If the substrate under the adhesive is weak or poorly bonded, remove such areas down to well bonded, sound, clean substrate.

Wood

Platform GP is suitable for skimcoating well bonded (screwed & glued) APA rated, exterior grade wood floors free of deflection. Wood floors are required to be a minimum of 3/4", L/360 and comply to local building codes. No primer is required. Do not install over OSB, chipboard, Masonite, or surfaces non-APA rated, and/or non-dimensionally stable materials subject to swelling or movement.

Quarry & Ceramic Tile

Ensure waxes or sealers are stripped from the surface of the tiles. Abrade to a dull finish. Remove dust by vacuum. Consider utilizing Platform P360 for additional bond.

Gypsum Substrates

Platform GP is suitable for skimcoating and patching gypsum substrates. Ensure the substrate is sound, dry, stable, clean and free of any bond breaking materials (silicates, curing compounds, laitance, dirt). Mechanically remove weak surfaces, and any contaminants to sound concrete. Priming is not required unless the substrate is dusty or inherently weak, then consult the Platform P360 technical data sheet for details on priming porous substrates.

MIXING

Water: 5.5 qts. of water to 25 lb. bag
Mix Platform GP either in a full bag, or by 2 to 2 1/2 parts Platform GP to 1 part water.
Mix Method: ALWAYS utilize a drill and mix until material is thoroughly homogenous and lump free. Overwatering and/or under mixing will result in difficult placement and lower ultimate compressive strengths. Add designated clean, potable water to a clean mixing vessel, add the powder and mix mechanically until homogenous and lump free. Mix no more material than can be placed within 10 minutes. Do not remix with additional water.

DRY TIME PRIOR TO FLOOR COVERINGS

Platform GP does not self dry, you may use fans to accelerate drying. Depth of placement and ambient conditions will impact the dry time of the material. Material is typically dry in 30-45 minutes and ready for light sanding prior to application of flooring, or direct application of flooring.

LIMITED WARRANTY

Platform Performance Flooring Systems warrants to the initial purchaser only that the goods sold hereunder will be free from defects in material and workmanship and, except as otherwise set forth herein, will conform to the specifications provided. If any failure to meet this warranty appears within one year from the date of shipment of the goods, on the condition that Platform Performance Flooring Systems will correct any such failure by either replacing or repairing any defective goods, at Platform Performance Flooring Systems' option. The preceding paragraph sets forth the exclusive remedy for all claims based on failure of or defect in the goods sold hereunder, whether such failure or defect arises before or during the warranty period and whether a claim, however instituted, is based on contract, indemnity, warranty, tort (including negligence), strict liability or otherwise. The forgoing warranty is exclusive and is in lieu of all other warranties whether written, oral, implied or statutory.

24 HOUR EMERGENCY: CHEMTREC®

1-800-424-9300

NON-TOXIC and NON-FLAMMABLE

Keep container closed and keep away from children. May cause slight eye abrasion or irritation if spilled or rubbed in eyes. Flush thoroughly with water.

If taken internally, call a physician.

Published technical data & instructions are subject to change without notice. Please contact Platform Performance Flooring Systems for the most current technical data, safety data & application instructions.

Technical Assistance:

Visit our website: platformperformance.com
or call

1-800-227-3434

